

Project Information

Client Name:	Basecrete Technologies, LLC	
	8255 Consumer Ct,	
	Sarasota, FL 34240	
Attention:	Kael Barbour	
Laboratory work order No:	22E0259	
Client Factory ID:		
Product Type:	Cementitious Waterproof Membran	
Model # :	Basecrete	
Testing Standard :	NSF/ANSI/CAN 61	
Testing Standard Section:	5	
Testing Standard Year:	2020	
Project Type:	Initial Certification	
Report Date:	7/6/2022	
Prepared By:	Cameron Song	
TIC's EPA 524.2 and EPA625	Pass	
Leaching Time	24	
Normalization Factor Organics	0.0390	
Normalization Factor Metal	0.039	
Date Entered :	7/5/2022	
Method Regulated Metal Analysis:	EPA 200.8	
Date of metals Analysis:	6/9/2022	
Method Non regulated metal Analysis:	N/A	
Date of non reg. metals Analysis:		
Date Pb for NSF/ANSI 372 Analysis:	N/A	
NSF/ANSI 372 standard Year:		
VOC Method:	EPA 524.2	
Date of VOC Analysis:	6/22/2022	
SVOC Method:	EPA 625.1	
Date of SVOC Analysis:	6/23/2022	
Residential or Commercial:		
Evaluated By:	Cameron Song	
Section 5 only (Tank or Pipe):	Tank	
Sample Size:		
Section 5 Additional Information		
Surface area-to-volume ratio (in²/L)	Nominal Capacity	
2.9	8,000	

Quality Control Results- Metal

Client Name: Basecrete Technologies, LLC

Testing Standard:

Project #: 22E0259

Section:

Product Type: Cementitious Waterproof Membrane

Year:

Model: Basecrete

Parameter	RL	Laboratory Reagent Blank		Laboratory Fortified Blank		
		Units	Result	Result %	Lower Limit	Upper Limit
Antimony		ug/L			85%	115%
Arsenic		ug/L			85%	115%
Barium		ug/L			85%	115%
Beryllium		ug/L			85%	115%
Bismuth		ug/L			85%	115%
Cadmium		ug/L			85%	115%
Chromium		ug/L			85%	115%
Copper		ug/L			85%	115%
Lead		ug/L			85%	115%
Mercury		ug/L			85%	115%
Nickel		ug/L			85%	115%
Selenium		ug/L			85%	115%
Thallium		ug/L			85%	115%
Zinc		ug/L			85%	115%
Tin		ug/L			85%	115%
Silver		ug/L			85%	115%
Aluminum		ug/L			85%	115%
Titanium		ug/L			85%	115%
Vanadium		ug/L			85%	115%
Manganese		ug/L			85%	115%
Cobalt		ug/L			85%	115%
Strontium		ug/L			85%	115%
Silicon		ug/L			85%	115%
Zirconium		ug/L			85%	115%

RL = Reporting Limit

A/na = Acceptable / Not Acceptable

Quality Control Results- SVOC

Client Name: Basecrete Technologies, LLC Testing Standard: NSF/ANSI/CAN 61
 Project #: 22E0259 Section: 5
 Product Type: Cementitious Waterproof Membrane Year: 2020
 Model: Basecrete

Parameter	RL	Laboratory Reagent Blank		Laboratory Fortified Blank		QC Quality (A/na)*
		Units	Result	Result %	Lower Limit	
1,2,4-Trichlorobenzene	2	ug/L	ND			A
1,3-Dichlorobenzene	2	ug/L	ND			A
1,4-Dichlorobenzene	2	ug/L	ND			A
2,4-Dinitrotoluene	2	ug/L	ND			A
4-Chloro-3-methylphenol	2	ug/L	ND			A
4-Nitrophenol	2	ug/L	ND			A
Acenaphthene	2	ug/L	ND			A
propylamine	2	ug/L	ND			A
Phenol	2	ug/L	ND			A
Pyrene	2	ug/L	ND			A

RL = Reporting Limit
 A/na = Acceptable / Not Acceptable

Quality Control Results- VOC

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Section: 5

Product Type: Cementitious Waterproof Membrane

Year: 2020

Model: Basecrete

Parameter	RL	Laboratory Reagent Blank		Laboratory Fortified Blank		QC Quality (A/na)*	
		Units	Result	Result %	Lower Limit		Upper Limit
Chloromethane	0.5	ug/L	ND		70	130	na
Dichlorodifluoromethane	0.5	ug/L	ND		70	130	na
Vinyl Chloride	0.5	ug/L	ND		70	130	na
Bromomethane	0.5	ug/L	ND		70	130	na
Chloroethane	0.5	ug/L	ND		70	130	na
Trichlorofluoromethane	1.0	ug/L	ND		70	130	na
1,1,2-Trichlorotrifluoroethane	0.5	ug/L	ND		70	130	na
Acrolein	2.0	ug/L	ND		70	130	na
Acetone	5.0	ug/L	ND		70	130	na
1,1-Dichloroethene	0.5	ug/L	ND		70	130	na
Methylene chloride	0.5	ug/L	ND		70	130	na
Methyl tert-Butyl Ether	0.5	ug/L	ND		70	130	na
tert-Butyl Alcohol	2.5	ug/L	ND		70	130	na
trans-1,2-Dichloroethene	0.5	ug/L	ND		70	130	na
Acrylonitrile	1.0	ug/L	ND		70	130	na
1,1-Dichloroethane	0.5	ug/L	ND		70	130	na
Diisopropyl ether	0.5	ug/L	ND		70	130	na
Ethyl tert-Butyl Ether	0.5	ug/L	ND		70	130	na
cis-1,2-Dichloroethene	0.5	ug/L	ND		70	130	na
2-Butanone	2.0	ug/L	ND		70	130	na
Chloroform	0.5	ug/L	ND		70	130	na
1,1,1-Trichloroethane	0.5	ug/L	ND		70	130	na
2,2-Dichloropropane	0.5	ug/L	ND		70	130	na
Carbon Tetrachloride	0.5	ug/L	ND		70	130	na
Benzene	0.5	ug/L	ND		70	130	na
1,2-Dichloroethane	0.5	ug/L	ND		70	130	na
Bromochloromethane	0.5	ug/L	ND		70	130	na
Trichloroethene	0.5	ug/L	ND		70	130	na
1,2-Dichloropropane	0.5	ug/L	ND		70	130	na
Bromodichloromethane	0.5	ug/L	ND		70	130	na
1,1-Dichloropropene	0.5	ug/L	ND		70	130	na
cis-1,3-Dichloropropene	0.5	ug/L	ND		70	130	na
4-Methyl-2-Pentanone	0.5	ug/L	ND		70	130	na
tert-Amyl methyl ether	0.5	ug/L	ND		70	130	na
Toluene	0.5	ug/L	ND		70	130	na
trans-1,3-Dichloropropene	0.5	ug/L	ND		70	130	na
1,1,2-Trichloroethane	0.5	ug/L	ND		70	130	na
Dibromomethane	0.5	ug/L	ND		70	130	na
Tetrachloroethene	0.5	ug/L	ND		70	130	na
2-Hexanone	1.0	ug/L	ND		70	130	na
Dibromochloromethane	0.5	ug/L	ND		70	130	na
Chlorobenzene	0.5	ug/L	ND		70	130	na
Ethylbenzene	0.5	ug/L	ND		70	130	na

Quality Control Results- VOC

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Section: 5

Product Type: Cementitious Waterproof Membrane

Year: 2020

Model: Basecrete

1,1,1,2-Tetrachloroethane	0.5	ug/L	ND		70	130	na
m,p-Xylene	1.0	ug/L	ND		70	130	na
o-Xylene	0.5	ug/L	ND		70	130	na
Styrene	0.5	ug/L	ND		70	130	na
1,3-Dichloropropane	0.5	ug/L	ND		70	130	na
Bromoform	0.5	ug/L	ND		70	130	na
1,3-Dichlorobenzene	0.5	ug/L	ND		70	130	na
1,4-Dichlorobenzene	0.5	ug/L	ND		70	130	na
1,2-Dibromoethane	0.5	ug/L	ND		70	130	na
1,2-Dichlorobenzene	0.5	ug/L	ND		70	130	na
1,1,1,2-Tetrachloroethane	0.5	ug/L	ND		70	130	na
Isopropylbenzene	0.5	ug/L	ND		70	130	na
Bromobenzene	0.5	ug/L	ND		70	130	na
n-Propylbenzene	0.5	ug/L	ND		70	130	na
1,2,3-Trichloropropane (TCP)	0.5	ug/L	ND		70	130	na
2-Chlorotoluene	0.5	ug/L	ND		70	130	na
1,3,5-Trimethylbenzene	0.5	ug/L	ND		70	130	na
4-Chlorotoluene	0.5	ug/L	ND		70	130	na
tert-Butylbenzene	0.5	ug/L	ND		70	130	na
1,2,4-Trimethylbenzene	0.5	ug/L	ND		70	130	na
sec-Butylbenzene	0.5	ug/L	ND		70	130	na
4-Isopropyltoluene	0.5	ug/L	ND		70	130	na
n-Butylbenzene	0.5	ug/L	ND		70	130	na
1,2-Dibromo-3-chloropropane	0.5	ug/L	ND		70	130	na
1,2,4-Trichlorobenzene	0.5	ug/L	ND		70	130	na
Hexachlorobutadiene	0.5	ug/L	ND		70	130	na
Naphthalene	0.5	ug/L	ND		70	130	na
1,2,3-Trichlorobenzene	0.5	ug/L	ND		70	130	na
Carbon Disulfide	0.5	ug/L	ND		70	130	na

RL = Reporting Limit

A/na = Acceptable / Not Acceptable

pH 5 LEACHATE WATER - METALS TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Section: 5

Product Type: Cementitious Waterproof Membrane

Year: 2020

Model: Basecrete

Size:

Normalizatin Factor: 0.04

Parameter	CAS#	Blank Corrected Result (ug/L)	Norm. Conc. (ug/L)	Satisfies Requirements	SPAC (ug/L)
Antimony	7440-36-0				0.6
Arsenic	7440-38-2				1
Barium	7440-39-3				200
Beryllium	7440-41-7				0.4
Bismuth	7440-69-9				40
Cadmium	7440-43-9				0.5
Chromium	7440-47-3	54.900	2.141	Yes	10
Copper	7440-50-8	5.536	0.216	Yes	130
Lead	7439-92-1				0.5
Mercury	7439-97-6				0.2
Nickel	7440-02-0				20
Selenium	7782-49-2	12.500	0.488	Yes	5
Thallium	7440-28-0				0.2
Zinc	7440-66-6				300
Tin	7440-31-5				400
Silver	7440-22-4				10
Aluminum	7429-90-5				2000
Titanium	7440-32-6				9000
Vanadium	7440-62-2				3
Manganese	7439-96-5				30
Cobalt	7440-48-4				0.7
Strontium	7440-24-6				400
Silicon	7440-21-3				100
Zirconium	7440-67-7				70

pH 10 LEACHATE WATER - METALS TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Section: 5

Product Type: Cementitious Waterproof Membrane

Year: 2020

Model: Basecrete

Size:

Normalization Factor: 0.04

Parameter	CAS#	Blank corrected Result (ug/L)	Norm. Conc. (ug/L)	Satisfies Requirements	SPAC (ug/L)
Antimony	7440-36-0				0.6
Arsenic	7440-38-2				1
Barium	7440-39-3	129.782	5.061	Yes	200
Beryllium	7440-41-7				0.4
Bismuth	7440-69-9				40
Cadmium	7440-43-9				0.5
Chromium	7440-47-3	57.006	2.223	Yes	10
Copper	7440-50-8	4.439	0.173	Yes	130
Lead	7439-92-1				0.5
Mercury	7439-97-6				0.2
Nickel	7440-02-0				20
Selenium	7782-49-2	13.700	0.534	Yes	5
Thallium	7440-28-0				0.2
Zinc	7440-66-6				300
Tin	7440-31-5				400
Silver	7440-22-4				10
Aluminum	7429-90-5				2000
Titanium	7440-32-6				9000
Vanadium	7440-62-2				3
Manganese	7439-96-5				30
Cobalt	7440-48-4				0.7
Strontium	7440-24-6				400
Silicon	7440-21-3				100
Zirconium	7440-67-7				70

Leachate Water - VOC TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard:

NSF/ANSI/CAN 61

Project #: 22E0259

Year: 2020

Product Type: Cementitious Waterproof Membrane

Section: 5

Model: Basecrete

Prepared By: Cameron Song

Size:

Normalization Factor : 0.039

Parameter	Blank corrected Lab. Result	Normalized Lab. Results (µg/L)	RL (µg/L)	Normalized RL (µg/L)	SPAC	Satisfies Requirements
Chloromethane	ND	<RL	0.50	0.02	3	YES
Dichlorodifluoromethane	ND	<RL	0.50	0.02	0	NO**
Vinyl Chloride	ND	<RL	0.50	0.02	0	NO**
Bromomethane	ND	<RL	0.50	0.02	1	YES
Chloroethane	ND	<RL	0.50	0.02	0	NO**
Trichlorofluoromethane	ND	<RL	1.00	0.04	200	YES
1,1,2-Trichlorotrifluoroethane	ND	<RL	0.50	0.02	0	YES
Acrolein	ND	<RL	2.00	0.08	0	NO**
Acetone	ND	<RL	5.00	0.20	600	YES
1,1-Dichloroethene	ND	<RL	0.50	0.02	1	YES
Methylene chloride	ND	<RL	0.50	0.02	1	YES
Methyl tert-Butyl Ether	ND	<RL	0.50	0.02	0	YES
tert-Butyl Alcohol	ND	<RL	2.50	0.10	900	YES
trans-1,2-Dichloroethene	ND	<RL	1.00	0.04	10	YES
Acrylonitrile	ND	<RL	0.50	0.02	0	NO**
1,1-Dichloroethane	ND	<RL	0.50	0.02	0	NO**
Diisopropyl ether	ND	<RL	0.50	0.02	0	YES
Ethyl tert-Butyl Ether	ND	<RL	0.50	0.02	2000	YES
cis-1,2-Dichloroethene	ND	<RL	0.50	0.02	7	YES
2-Butanone	ND	<RL	2.00	0.08	400	YES
Chloroform	0.18	0.00702	0.50	0.02	8	YES
1,1,1-Trichloroethane	ND	<RL	0.50	0.02	20	YES
2,2-Dichloropropane	ND	<RL	0.50	0.02	0	YES
Carbon Tetrachloride	ND	<RL	0.50	0.02	1	YES
Benzene	ND	<RL	0.50	0.02	1	YES
1,2-Dichloroethane	ND	<RL	0.50	0.02	1	YES
Bromochloromethane	ND	<RL	0.50	0.02	9	YES
Trichloroethene	ND	<RL	0.50	0.02	1	YES
1,2-Dichloropropane	ND	<RL	0.50	0.02	1	YES
Bromodichloromethane	0.13	0.00507	0.50	0.02	8	YES
1,1-Dichloropropene	ND	<RL	0.50	0.02	0	NO**
cis-1,3-Dichloropropene	ND	<RL	0.50	0.02	0	NO**
4-Methyl-2-Pentanone	ND	<RL	0.50	0.02	700	YES
tert-Amyl methyl ether	ND	<RL	0.50	0.02	0	NO**
Toluene	ND	<RL	0.50	0.02	6	YES
trans-1,3-Dichloropropene	ND	<RL	0.50	0.02	0	NO**
1,1,2-Trichloroethane	ND	<RL	0.50	0.02	1	YES
Dibromomethane	ND	<RL	0.50	0.02	0	YES
Tetrachloroethene	ND	<RL	0.50	0.02	1	YES
2-Hexanone	ND	<RL	1.00	0.04	4	YES
Dibromochloromethane	ND	<RL	0.50	0.02	8	YES

Leachate Water - VOC TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Year: 2020

Product Type: Cementitious Waterproof Membrane

Section: 5

Model: Basecrete

Prepared By: Cameron Song

Size:

Normalization Factor : 0.039

Parameter	Blank corrected Lab. Result	Normalized Lab. Results (µg/L)	RL (µg/L)	Normalized RL (µg/L)	SPAC	Satisfies Requirements
Chlorobenzene	0.48	0.01872	0.50	0.02	10	YES
Ethylbenzene	ND	<RL	0.50	0.02	14	YES
1,1,1,2-Tetrachloroethane	ND	<RL	0.50	0.02	1	YES
m,p-Xylene	ND	<RL	0.50	0.02	0	YES
o-Xylene	ND	<RL	0.50	0.02	9	YES
Styrene	ND	<RL	0.50	0.02	10	YES
1,3-Dichloropropane	ND	<RL	0.50	0.02	10	YES
Bromoform	ND	<RL	0.50	0.02	8	YES
1,3-Dichlorobenzene	ND	<RL	0.50	0.02	60	YES
1,4-Dichlorobenzene	ND	<RL	0.50	0.02	8	YES
1,2-Dibromoethane	ND	<RL	0.50	0.02	0	NO**
1,2-Dichlorobenzene	ND	<RL	0.50	0.02	60	YES
1,1,2,2-Tetrachloroethane	ND	<RL	0.50	0.02	0	NO**
Isopropylbenzene	ND	<RL	0.50	0.02	70	YES
Bromobenzene	ND	<RL	0.50	0.02	0	NO**
n-Propylbenzene	ND	<RL	0.50	0.02	20	YES
1,2,3-Trichloropropane (TCP)	ND	<RL	0.50	0.02	4	YES
2-Chlorotoluene	ND	<RL	0.50	0.02	10	YES
1,3,5-Trimethylbenzene	ND	<RL	0.50	0.02	20	YES
4-Chlorotoluene	ND	<RL	0.50	0.02	10	YES
tert-Butylbenzene	ND	<RL	0.50	0.02	20	YES
1,2,4-Trimethylbenzene	ND	<RL	0.50	0.02	20	YES
sec-Butylbenzene	ND	<RL	0.50	0.02	20	YES
4-Isopropyltoluene	ND	<RL	0.50	0.02	20	YES
n-Butylbenzene	ND	<RL	0.50	0.02	20	YES
1,2-Dibromo-3-chloropropane	ND	<RL	0.50	0.02	0	NO**
1,2,4-Trichlorobenzene	ND	<RL	0.50	0.02	7	YES
Hexachlorobutadiene	ND	<RL	0.50	0.02	0	NO**
Naphthalene	0.1	0.0039	0.50	0.02	10	YES
1,2,3-Trichlorobenzene	0.2	0.0078	0.50	0.02	0	YES
Carbon Disulfide	ND	<RL	0.50	0.02	70	YES

Note: ** The result is non-detected, but the RL is higher than the SPAC value

Leachate Water - SVOC TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Year: 2020

Product Type: Cementitious Waterproof Membrane

Section: 5

Model: Basecrete

Prepared By: Cameron Song

Size:

Normalization Factor = 0.039

Parameter	Blank corrected Result (µg/L)	Normalized Results (µg/L)	RL (µg/L)	Normalized RL (µg/L)	SPAC	Satisfies Requirements
1,2,4-Trichlorobenzene	ND	<RL	2	0.078	7	YES
1,2-Dichlorobenzene	ND	<RL	2	0.078	60	YES
1,3-Dichlorobenzene	ND	<RL	2	0.078	60	YES
1,4-Dichlorobenzene	ND	<RL	2	0.078	7.5	YES
2,4,5-Trichlorophenol	ND	<RL	2	0.078	70	YES
2,4,6-Trichlorophenol	ND	<RL	2	0.078	0.5	NO**
2,4-Dichlorophenol	ND	<RL	2	0.078	5	YES
2,4-Dimethylphenol	ND	<RL	2	0.078	10	YES
2,4-Dinitrophenol	ND	<RL	2	0.078	0	YES
2,4-Dinitrotoluene	ND	<RL	2	0.078	0.05	NO**
2,6-Dinitrotoluene	ND	<RL	2	0.078	0.05	NO**
2-Chloronaphthalene	ND	<RL	2	0.078	60	YES
2-Chlorophenol	ND	<RL	2	0.078	0	YES
2-Methylnaphthalene	ND	<RL	2	0.078	3	YES
2-Methylphenol	ND	<RL	2	0.078	40	YES
2-Nitroaniline	ND	<RL	2	0.078	0	YES
2-Nitrophenol	ND	<RL	2	0.078	0.3	NO**
3,3-Dichlorobenzidine	ND	<RL	4	0.156	0.08	NO**
3-Nitroaniline	ND	<RL	2	0.078	0	YES
4,6-Dinitro-2-methylphenol	ND	<RL	2	0.078	0	YES
4-Bromophenyl phenyl ether	ND	<RL	2	0.078	0	YES
4-Chloro-3-methylphenol	ND	<RL	2	0.078	70	YES
4-Chloroaniline	ND	<RL	2	0.078	0	YES
4-Chlorophenyl phenyl ether	ND	<RL	2	0.078	0.3	NO**
4-Methylphenol	ND	<RL	2	0.078	4	YES
4-Nitroaniline	ND	<RL	2	0.078	4	YES
4-Nitrophenol	ND	<RL	2	0.078	6	YES
Acenaphthene	ND	<RL	2	0.078	0.3	NO**
Acenaphthylene	ND	<RL	2	0.078	0.3	NO**
Anthracene	ND	<RL	2	0.078	0.3	NO**
1,2-Diphenylhydrazine/Azobenzene	ND	<RL	2	0.078	0.05	NO**
Benzidine	ND	<RL	4	0.156	0.0002	NO**
Benzo(a)anthracene	ND	<RL	2	0.078	0.02	NO**
Benzo(a)pyrene	ND	<RL	2	0.078	0.004	NO**
Benzo(b)fluoranthene	ND	<RL	2	0.078	0.02	NO**
Benzo(g,h,i)perylene	ND	<RL	2	0.078	0	YES
Benzo(k)fluoranthene	ND	<RL	2	0.078	0	YES
Benzyl alcohol	ND	<RL	2	0.078	3000	YES

Leachate Water - SVOC TOX Data Sheet

Client Name: Basecrete Technologies, LLC

Testing Standard: NSF/ANSI/CAN 61

Project #: 22E0259

Year: 2020

Product Type: Cementitious Waterproof Membrane

Section: 5

Model: Basecrete

Prepared By: Cameron Song

Size:

Normalization Factor = 0.039

Parameter	Blank corrected Result (µg/L)	Normalized Results (µg/L)	RL (µg/L)	Normalized RL (µg/L)	SPAC	Satisfies Requirements
Bis(2-chloroethoxy)methane	ND	<RL	2	0.078	0	YES
Bis(2-chloroethyl)ether	ND	<RL	2	0.078	0.03	NO**
Bis(2-chloroisopropyl)ether	ND	<RL	2	0.078	0	YES
Bis(2-ethylhexyl)phthalate	0.73	0.02847	2	0.078	0.6	YES
Butylbenzylphthalate	ND	<RL	2	0.078	100	YES
Carbazole	ND	<RL	2	0.078	0.3	NO**
Chrysene	ND	<RL	2	0.078	0	YES
Dibenzo(a,h)anthracene	ND	<RL	2	0.078	0	YES
Dibenzofuran	ND	<RL	2	0.078	0	YES
Diethylphthalate	ND	<RL	2	0.078	600	YES
Dimethylphthalate	ND	<RL	2	0.078	50	YES
Di-n-butyl phthalate	ND	<RL	2	0.078	70	YES
Di-n-octylphthalate	ND	<RL	2	0.078	0	YES
Fluoranthene	ND	<RL	2	0.078	0.3	NO**
Fluorene	ND	<RL	2	0.078	30	YES
Hexachlorobenzene	ND	<RL	2	0.078	0.1	NO**
Hexachlorobutadiene	ND	<RL	2	0.078	0.4	NO**
Hexachlorocyclopentadiene	ND	<RL	2	0.078	5	YES
Hexachloroethane	ND	<RL	2	0.078	0.9	NO**
Indeno(1,2,3-cd)pyrene	ND	<RL	2	0.078	0	YES
Isophorone	ND	<RL	2	0.078	40	YES
Naphthalene	ND	<RL	2	0.078	10	YES
Nitrobenzene	ND	<RL	2	0.078	1	NO**
N-Nitrosodimethylamine	ND	<RL	2	0.078	0.0007	NO**
N-Nitroso-di-n-propylamine	ND	<RL	2	0.078	0.005	NO**
N-Nitrosodiphenylamine	ND	<RL	2	0.078	7	YES
Pentachlorophenol	ND	<RL	2	0.078	0.1	NO**
Phenanthrene	ND	<RL	2	0.078	0.3	NO**
Phenol	7.9	0.3081	2	0.078	200	YES
Pyrene	ND	<RL	2	0.078	0.3	NO**

Note: ** The result is non-detected, but the MDL is higher than the SPAC value